

**REMARKS**

The substitute specification together with the amended claims place the present U.S. national phase application in better form for examination on the merits.

Also attached hereto is an Abstract of the Disclosure presented on a separate sheet in conformity with the rules of practice.

Based upon the specification and claim amendments to this national phase application, it is believed that the amended specification and amended claims conform with U.S. formal requirements. Additionally, the amended claims as hereinabove presented conform in substance with the corresponding amended claims that were examined in the international application. And based upon the acceptance by the International Preliminary Examining Authority of the invention as it was claimed in the amended claims that were presented in the international application as meeting each of the novelty, the inventive step, and the industrial applicability criteria set forth in the Patent Cooperation Treaty, the claims as amended above are believed to conform with both U.S. formal and U.S. substantive requirements, and they are therefore believed to be in allowable form. Accordingly, an early Notice of Allowance is in order and is respectfully solicited.

Should the examiner have any question after considering this Preliminary Amendment, he is cordially invited to telephone the undersigned

attorney so that any such question can be quickly resolved in order that the present application can proceed toward allowance.

Respectfully submitted,

A handwritten signature in black ink, appearing to read 'Alfred J. Mangels', with a long horizontal flourish extending to the right.

October 3, 2004

Alfred J. Mangels  
Reg. No. 22,605  
4729 Cornell Road  
Cincinnati, Ohio 45241  
Tel.: (513) 469-0470

Attachments: Attachment A  
Attachment B  
Abstract of the Disclosure

**ATTACHMENT B**

**SUBSTITUTE SPECIFICATION**

(Showing All Changes from the Specification in Published International Application No.  
PCT/SE03/00379, Publication No. WO 03/087014 A1)

**METHOD OF MAKING A HEATING ELEMENT OF THE MOLYBDENUM SILICIDE  
TYPE AND A HEATING ELEMENT**

**BACKGROUND OF THE INVENTION**

**FIELD OF THE INVENTION**

The present invention relates to a method of manufacturing a heating element of the molybdenum silicide type and also to a heating element.

**DESCRIPTION OF THE RELATED ART**

An electrical resistance element of the molybdenum silicide type is described in Swedish Patent Specifications 0003512-1 and 0004329-9. According to patent specification 0003512-1 the resistance material of the heating element includes  $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$   ~~$\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$  which is caused to contain aluminium~~ contains aluminum to an extent at which the formation of pest is essentially prevented.

It has been found that when such material is operated in a temperature range of 400 - 600°C no pest, or only a slight amount of pest, is formed. Pest is formed by virtue of the formation of  ~~$\text{MoO}_3$~~   $\text{MoO}_3$  from  ~~$\text{MoSi}_2$~~   $\text{MoSi}_2$  and  ~~$\text{O}_2$~~   $\text{O}_2$ .

The reason why the formation of pest is significantly reduced or is eliminated is due to the formation of  ~~$\text{Al}_2\text{O}_3$~~   $\text{Al}_2\text{O}_3$  on the surface of the element.

According to one preferred embodiment x ~~is caused to lie~~ lies in the range of 0.2 - 0.6.

The other patent specification, 0004329-9, teaches a method of increasing the useful life span of heating elements that consist chiefly of molybdenum silicide and alloys of this basic material where the element operates at high temperatures.

According to ~~this~~ that patent specification, the heating element ~~is caused to contain aluminium~~ contains aluminum to an extent which is sufficient to maintain a stable, slowly growing layer of ~~aluminium~~ aluminum oxide on the surface of the heating element.

According to a preferred embodiment the heating element material ~~is caused to contain~~ contains  $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$   $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$  where x lies in the range of 0.2 - 0.6.

A material of the molybdenum silicide type that contains ~~aluminium~~ aluminum has been found to possess improved corrosion properties at both low and high temperatures.

Such material is often produced by mixing  $\text{MoSi}_2$   $\text{MoSi}_2$  powder with oxidic raw material, such as aluminosilicates. When the raw material is bentonite clay, there is obtained a relatively low melting point which contributes towards so-called smelt phase sintering, which results in a dense material that contains  $\text{MoSi}_2$   $\text{MoSi}_2$  and a proportion of ~~aluminium~~ aluminum silicate corresponding to 15 - 20 percent by volume.

Bentonite clay has different compositions. Some bentonites include 60% by weight  $\text{SiO}_2$   $\text{SiO}_2$  while some contain somewhat more than 70% by weight  $\text{SiO}_2$   $\text{SiO}_2$ . Although the  $\text{Al}_2\text{O}_3$   $\text{Al}_2\text{O}_3$  content varies, it normally lies between 13 - 20% by weight. The melting point varies between about 1200 - 1400°C.

Bentonite clay that contains chiefly  $\text{SiO}_2$   $\text{SiO}_2$  can be used in the production of heating elements containing  $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$   $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ . When sintering with an Al-

alloyed silicide there takes place a chemical exchange reaction in which the greater affinity of the oxygen to Al than to Si results in Si leaving the ~~aluminium~~ aluminum silicate and entering the silicide as a result of Al leaving the silicide and being sucked taken up by the oxide phase. This exchange reaction also contributes towards improved sintering properties of the composite material. The final material contains  $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$   ~~$\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$~~  that is substantially ~~deplete~~ depleted of Al, where the oxide phase contains  ~~$\text{Al}_2\text{O}_3$~~   $\text{Al}_2\text{O}_3$  in all essentials.

The standard procedure of manufacture involves mixing molybdenum, silicon, and ~~aluminium~~ aluminum in powder form and firing the powder mix normally under a shielding gas atmosphere. This results in a cake of the material  ~~$\text{Mo}(\text{Si}_{1-y}\text{Al}_y)_2$~~   $\text{Mo}(\text{Si}_{1-y}\text{Al}_y)_2$ , where y is larger than x in the above formula as a result of said exchange reaction. The reaction is exothermic. The cake is then crushed and ground down to a fine particle size normally in the order of 1 - 20  $\mu\text{m}$ . ~~This~~ The resulting powder is mixed with bentonite clay ~~such as~~ to form a wet ceramic material. The material is extruded and dried to a rod form whose diameter corresponds to the diameter of the subsequent element. The material is then sintered at a temperature that exceeds the melting temperature of the ~~including~~ included components.

However, there is a drawback with an a heating element of ~~this~~ that kind. The problem is that the oxide that forms on the surface of the element, namely  ~~$\text{Al}_2\text{O}_3$~~   $\text{Al}_2\text{O}_3$ , sometimes peels away or flakes off, i.e., loosens from the surface of the element, in the case of cyclic operation.

A peeling oxide gives poorer protection against continued oxidation of ~~aluminium~~ aluminum which becomes impoverished in the outer surface of the element

more quickly. Moreover, a peeling oxide can contaminate the oven in which the element is fitted, with the risk that performance and the appearance of products heat treated in ovens that have such elements will be significantly impaired. This restricts the use of such elements in heating processes.

This problem is solved by the present invention.

### SUMMARY OF THE INVENTION

The present invention thus relates to a method of producing a heating element substantially ~~comprising~~ of the molybdenum silicide type and alloys of this basic material, and is characterized by producing a material that substantially contains  $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$   $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$  and  $\text{Al}_2\text{O}_3$   $\text{Al}_2\text{O}_3$  by mixing a molybdenum aluminosilicide  $\text{Mo}(\text{Si}_{1-y}\text{Al}_y)_2$   $\text{Mo}(\text{Si}_{1-y}\text{Al}_y)_2$  with  $\text{SiO}_2$   $\text{SiO}_2$  wherein  $\text{SiO}_2$   $\text{SiO}_2$  has a purity of at least 98%.

Further, the invention relates to a heating element of the kind ~~and with the main features as indicated in claim 5~~ disclosed type in which Re or W is partially substituted for molybdenum in the  $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$  material.

The invention will now be described in more detail in the following description.

### DESCRIPTION OF THE PREFERRED EMBODIMENTS

In accordance with the invention, a heating element that ~~consists~~ is composed chiefly of molybdenum silicide ~~type~~ and alloys of this basic material is produced by mixing a powder that chiefly contains  $\text{Mo}(\text{Si}_{1-y}\text{Al}_y)_2$   $\text{Mo}(\text{Si}_{1-y}\text{Al}_y)_2$  with highly pure  $\text{SiO}_2$   $\text{SiO}_2$ . Pure silicon dioxide has a melting temperature of about ~~1700°C~~ 1700 °C.

When using  $\text{SiO}_2$   $\text{SiO}_2$ , however, said exchange reaction between Si in the oxide and Al in the silicide results in a high density sintered product.

The mentioned  $\text{SiO}_2$   $\text{SiO}_2$  can be present as pure  $\text{SiO}_2$   $\text{SiO}_2$  or as an ~~aluminium~~ aluminum silicate of high purity. However,  $\text{SiO}_2$   $\text{SiO}_2$  can be included in silicates in which other substances in the silicate have properties which prevent the molybdenum silicide from being alloyed with the substance or substances concerned and with which the symmetry of crystal lattice of the molybdenum silicide will be retained. Mullite and sillimanite are examples of conceivable ~~material~~ materials in this regard.

The present invention thus replaces the bentonite clay with silicon dioxide, therewith excluding the transfer of impurities in the bentonite clay, such as Mg, Ca, Fe, Na, and K, to the heating element, thus eliminating the negative effects of such impurities on the function of said element.

It is possible to partly substitute molybdenum with Re or W in the material  ~~$\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$~~   $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$  without changing the symmetry of the crystal lattice.

It has been found surprisingly that there is obtained with low contaminant contents an oxide which does not peel after cyclic operation between room temperature and high temperatures, for instance 1500 °C.

According to one embodiment x is caused to lie in the range of 0.4 - 0.6.

According to one preferred embodiment x is caused to lie in the range of 0.45 - 0.55.

The present invention thus solves the problem mentioned in the introduction and enables the present heating element to be used beneficially in ovens without detriment to the material treated in the oven.

The present invention shall not be considered to be limited to the ~~aforedescribed~~ above-described embodiments, since variations can be made within the scope of the accompanying claims.



**CLAIMS**

What is claimed is: